



NO.	Type	Type	尺寸(Unit: mm)								磁心参数				Al-value (nH/N <sup>2</sup> )±25 %						功耗Max (W/set)					重量 (g/set)	
			A	B	C	C1	D	E	F	F1	C1	Le	Ae	Ve	KP4	KP44	KP44A	KP47	KP90	KP95	KP4	KP44	KP44A	KP47	KP90		KP95
			(mm <sup>-1</sup> )	(mm)	(mm <sup>2</sup> )	(mm <sup>3</sup> )																					
EM23-1	EM2321	2	22.50±0.3	10.60±0.2	6.50±0.2		8.00±0.2	17.70±0.3	10.00±0.15	3.00±0.1	1.68	52.80	31.36	1656	1257	1257	1257	1309	1152	1728	0.97	0.89	0.80	0.76	0.89	0.89	8.43
EM31.8	EM31.8	2	31.80±0.4	13.40±0.15	5.10±0.25		8.40±0.15	21.70min	15.50±0.2	3.10±0.2	1.30	61.60	47.70	2937	1624	1624	1624	1692	1489	2233	1.75	1.60	1.44	1.37	1.60	1.60	15.20
EM43-1	EM43.444	2	43.40±0.6	22.10±0.2	8.00±0.3		17.00±0.2	33.50min	22.35±0.25	3.20±0.15	1.40	108.00	75.00	8136	1508	1508	1508	1571	1382	2073	4.72	4.31	3.90	3.70	4.31	4.31	41.00
EM44-1	EM4445	2	43.50±0.6	22.40±0.4	7.80±0.2		17.20±0.4	34.50±0.6	22.20±0.2	3.20±0.2	1.52	109.00	71.80	7843	1389	1389	1389	1447	1273	1910	4.63	4.23	3.83	3.64	4.23	4.23	40.30
EM49-1	EM4953	2	49.00±0.7	26.60±0.2	7.00±0.25		19.30±0.2	35.80±0.5	27+0.15/-0.35	3.50±0.25	1.30	122.00	93.00	11346	1624	1624	1624	1692	1489	2233	6.58	6.01	5.43	5.16	6.01	6.01	57.20
EM49-2	EM4959	2	49.00±0.7	29.60±0.2	7.00±0.25		22.30±0.2	35.80±0.6	27+0.15/-0.35	3.50±0.25	1.40	133.00	94.00	12560	1508	1508	1508	1571	1382	2073	7.02	6.41	5.80	5.51	6.41	6.41	61.00
EM49-3	EM4963	2	49.00±0.7	31.60±0.2	7.00±0.25		24.30±0.3	35.80±0.5	27+0.15/-0.35	3.50±0.25	1.20	141.00	102.00	13287	1759	1759	1759	1833	1613	2419	7.44	6.79	6.15	5.84	6.79	6.79	64.70
EM50-1A	EM5046	2	50.00±0.6	23.10±0.4	7.50±0.2		15.80±0.4	37.60±0.6	27.00±0.2	3.50±0.2	1.14	109.00	96.20	10496	1852	1852	1852	1929	1698	2546	6.10	5.57	5.04	4.78	5.57	5.57	53.00
EM50-2	EM5053	2	50.10±0.5	26.60±0.2	6.4+0.0/-0.20		19.30±0.15	35.50min	27.00±0.25	3.4+0.0/-0.20	1.32	121.40	92.30	11205	1605	1605	1605	1672	1471	2207	6.66	6.08	5.50	5.23	6.08	6.08	57.90
EM50-3	EM5035	2	50.10±0.5	17.55±0.2	6.4+0.15/-0.20		10.25±0.2	35.50min	27+0.15/-0.20	3.4+0.05/-0.20	0.94	85.37	90.60	7735	2246	2246	2246	2339	2059	3088	4.60	4.20	3.80	3.61	4.20	4.20	40.00
EM50.7-1	EM50.728	2	50.70±0.7	27.85±0.25	9.00±0.35		20.75±0.25	38.10±0.7	23.45±0.25	5.00±0.20	1.10	129.10	118.00	15234	1919	1919	1919	1999	1759	2639	8.81	8.04	7.28	6.91	8.04	8.04	76.60
EFD10 (EPC10)	EFD10/16	2	10.00+0.3/-0.15	8.20±0.075	3.00+0.1/-0.15		6.625±0.075	7.80+0.3/-0.15	4.05+0.05/-0.1	1.65+0.05/-0.1	5.28	35.80	6.78	243	400	400	400	416	367	550	0.15	0.14	0.12	0.12	0.14	0.14	1.31
EFD9.8-1	EFD9.8B	8	9.80+0.1/-0.2	3.3±0.1	9.5±0.15	8.8±0.14	1.1±0.05	6.3±0.15	4.0±0.12	8.5±0.15	0.39	13.47	34.57	466	5413	5413	5413	5639	4962	7443	0.31	0.28	0.25	0.24	0.28	0.28	2.67
EFD10.4-1	EFD10.4	7	10.4±0.2	5.1±0.1	9.0±0.2	8.35±0.2	3.0±0.1	6.0±0.15	4.4±0.15	8.2±0.20	0.60	21.83	36.35	794	3519	3519	3519	3665	3225	4838	0.46	0.42	0.38	0.36	0.42	0.42	4.02
EFD12.7-1	EM12.7B	1	12.7±0.3	6.4+0.2/-0.1	4.75±0.2		4.9+0.2/-0.1	9.7min	5.15±0.15	2.2±0.1	2.34	29.63	12.62	374	902	902	902	940	827	1241	0.23	0.21	0.19	0.18	0.21	0.21	2.00
EFD15-2	EFD15/15.2	4	15.00±0.40	7.60±0.15	4.65±0.15		5.60±0.25	11.00±0.35	5.30±0.15	2.40±0.10	2.38	34.00	14.30	485	887	887	887	924	813	1220	0.32	0.29	0.27	0.25	0.29	0.29	2.80
EFD15-3	EFD1513	2	15.5±0.30	6.6±0.20	5.0±0.30		4.6±0.25	12.15±0.30	6.3±0.25	2.3±0.20	1.90	31.90	16.50	526	869	869	869	869	846	1054	0.33	0.30	0.28	0.26	0.30	0.30	2.90
EFD16-1	EFD1615	2	16.25±0.40	7.40±0.20	4.80±0.20		5.30±0.20	12.40min	6.00±0.20	2.50±0.20	2.20	36.30	16.20	588	960	960	960	1000	880	1319	0.36	0.33	0.29	0.28	0.33	0.33	3.10
EFD16.5-1	EFD16.5-1/39	2	16.55±0.25	19.40±0.25	4.45±0.20		16.45±0.20	11.30min	5.80±0.20	2.80±0.30	4.32	79.39	18.39	1460	489	489	489	509	448	672	0.94	0.86	0.78	0.74	0.86	0.86	8.20
EFD20-1	EFD20/20	1	20.00±0.50	10.00±0.15	6.65±0.15		7.70±0.25	15.40±0.50	8.90±0.20	3.60±0.15	1.60	45.50	28.50	1297	1322	1322	1322	1377	1212	1818	0.85	0.78	0.70	0.67	0.78	0.78	7.40
EFD20-2	EFD20/23	5	20.0±0.55	11.60±0.15	5.40±0.15		9.30±0.20	15.40±0.35	8.90±0.20	3.60±0.15	2.00	51.64	25.64	1319	1056	1056	1056	1100	968	1451	0.81	0.74	0.67	0.63	0.74	0.74	7.00
EFD20-3	EFD20/25	2	20.50±0.50	12.50±0.3	4.00±0.15		9.50±0.20	15.50min	10.00±0.2	2.00±0.10	2.88	56.85	19.77	1124	733	733	733	764	672	1008	0.64	0.59	0.53	0.51	0.59	0.59	5.60
EFD20-4	EFD20/13	5	20.30±0.4	6.50±0.15	6.50±0.2		3.30±0.15	14.60±0.4	8.00±0.2	4.60±0.2	0.79	30.40	38.60	1173	2672	2672	2672	2784	2450	3674	0.71	0.65	0.59	0.56	0.65	0.65	6.20
EFD20-6	EFD20.4	1	20.40±0.35	10.20±0.15	6.65±0.15		7.90+0.2/-0.15	15.90±0.3	8.90+0.1/-0.20	3.60±0.15	1.55	48.00	31.00	1476	1362	1362	1362	1419	1249	1873	0.84	0.77	0.69	0.66	0.77	0.77	7.30
EFD21-2	EFD21/24	2	21.20±0.4	12.10±0.2	5.90±0.15		9.30±0.15	15.80min	9.20±0.2	3.30±0.1	1.92	56.60	29.50	1671	1100	1100	1100	1145	1008	1512	0.94	0.86	0.78	0.74	0.86	0.86	8.20
EFD21-3	EFD21/20.8	5	20.8±0.4	10.4±0.15	6.75±0.25		8.0±0.15	16.0min	8.9±0.2	3.6±0.25	1.63	49.60	30.50	1510	1295	1295	1295	1349	1187	1781	0.87	0.80	0.72	0.69	0.80	0.80	7.60
EFD22-1	EFD2229	5	22.0±0.3	14.65±0.15	7.4±0.15		11.65±0.15	16.0±0.3	9.6±0.15	4.2±0.15	1.50	64.72	41.90	2712	1407	1407	1407	1466	1290	1935	1.62	1.48	1.34	1.27	1.48	1.48	14.10
EFD22.5-1	EFD22.5/24	2	22.50±0.60	12.00±0.20	4.00±0.20		9.35±0.20	17.00±0.40	11.00±0.25	1.90±0.15	2.53	54.00	21.30	1150	834	834	834	869	765	1147	0.74	0.67	0.61	0.58	0.67	0.67	6.40
EFD25-1	EFD25/25	1	25.00±0.60	12.50±0.15	9.10±0.20		9.30±0.25	18.70±0.60	11.40±0.20	5.20±0.25	1.04	55.80	53.90	3008	2039	2039	2039	2124	1869	2804	1.91	1.74	1.58	1.50	1.74	1.74	16.60
EFD25-2	EFD25.5/25	1	25.50±0.50	12.50±0.15	9.20±0.20		9.30±0.25	19.30±0.50	11.40±0.20	5.20±0.15	0.98	57.00	58.00	3306	2154	2154	2154	2244	1975	2962	1.93	1.76	1.60	1.52	1.76	1.76	16.80
EFD25-3	EFD2525L	1	25.35±0.30	12.5±0.15	7.6±0.20		9.3±0.25	19.0±0.3	11.4±0.20	4.3±0.15	1.20	57.89	48.60	2816	1759	1759	1759	1833	1613	2419	1.66	1.51	1.37	1.30	1.51	1.51	14.40



NO.	Type	尺寸(Unit: mm)										磁心参数				Al-value (nH/N <sup>2</sup> )±25 %						重量 (g/set)					
		A	B	C	C1	D	E	F	F1	C1	Le	Ae	Ve	KP4	KP44	KP44A	KP47	KP90	KP95	KP4	KP44		KP44A	KP47	KP90	KP95	
EFD26-2	EFD2632	1	26.0±0.65	16.3±0.2	9.1±0.2	8.5REF	12.8±0.2	19.2±0.5	11.4±0.2	5.2±0.2	1.22	72.82	59.50	4332	1730	1730	1730	1803	1586	2379	2.54	2.32	2.10	1.99	2.32	2.32	22.10
EFD27.5-1	EFD27.5/22	3	27.50±0.4	11.00±0.2	5.00±0.2		8.00±0.15	21.50±0.4	15±0.2	2.00±0.15	1.91	56.92	29.87	1700	1105	1105	1105	1151	1013	1520	0.98	0.90	0.81	0.77	0.90	0.90	8.56
EFD27.5-2	EFD27.5/25	2	27.50±0.5	12.50±0.2	8.00±0.2		9.00±0.3	20.70min	11.50±0.2	4.30±0.2	1.17	58.90	51.00	3003	1804	1804	1804	1880	1654	2481	1.82	1.66	1.50	1.43	1.66	1.66	15.80
EFD30-1	EFD30/30	1	30.00±0.65	15.00±0.25	9.10±0.20		11.20±0.30	22.40±0.75	14.60±0.30	4.90±0.25	0.81	55.80	69.00	3850	2611	2611	2611	2719	2393	3590	2.67	2.44	2.20	2.09	2.44	2.44	23.20
EFD30-2	EFD30/35	1	30.00±0.65	17.5±0.25	9.10±0.20		13.7±0.30	22.40±0.75	14.60±0.30	4.90±0.25	1.07	68.00	73.00	4864	1973	1973	1973	2055	1809	2713	3.05	2.78	2.52	2.39	2.78	2.78	26.50
EFD30-3	EFD30/31	1	30.00±0.65	15.50±0.50	9.10±0.20		11.50±0.60	22.50±0.50	14.60±0.30	4.90±0.25	1.32	68.21	51.71	3527	1599	1599	1599	1666	1466	2199	2.82	2.57	2.33	2.21	2.57	2.57	24.50
EFD31-1	EFD31/30A	1	31.00±0.70	15.20±0.25	9.10±0.20		11.40±0.20	23.20min	14.60±0.20	4.90±0.15	0.97	68.64	70.39	4869	2176	2176	2176	2267	1995	2993	2.78	2.54	2.30	2.18	2.54	2.54	24.20
EFD31-2	EFD31/30B	1	30.60±0.6	15.2±0.30	9.00±0.2		11.40±0.30	24.10min	14.60±0.20	4.85±0.15	1.13	69.95	61.78	4322	1865	1865	1865	1943	1710	2564	2.60	2.37	2.15	2.04	2.37	2.37	22.60
EFD31-3	EFD3035	1	30.80±0.5	17.50±0.3	9.10±0.3		13.70±0.3	23.10min	14.60±0.3	4.85±0.15	1.20	79.60	65.40	5208	1759	1759	1759	1833	1613	2419	3.08	2.81	2.55	2.42	2.81	2.81	26.80
EFD31-4	EFD31/30	1	31.40±0.50	15.00±0.20	9.10±0.20		11.30±0.20	23.40min	14.60±0.20	4.90±0.15	0.98	67.62	68.70	4695	2154	2154	2154	2244	1975	2962	2.75	2.51	2.27	2.16	2.51	2.51	23.90
EFD32-1	EFD32/32	5	32.00±0.5	16.50±0.25	10.25±0.2		12.00±0.2	24.00±0.4	14.00±0.2	6.00±0.15	0.92	77.00	83.50	6429	2295	2295	2295	2390	2104	3155	3.62	3.31	2.99	2.84	3.31	3.31	31.50
EFD31-5	EFD31.4/30	1	31.40±0.50	15.2±0.20	9.10±0.25		11.30±0.20	23.40min	14.60±0.25	4.90±0.15	1.02	71.80	70.18	5039	2070	2070	2070	2156	1897	2846	3.00	2.74	2.48	2.36	2.74	2.74	26.13
EFD33-1	EFD3334	1	33.40±0.50	17.60±0.25	9.10±0.25		13.70±0.25	25.80±0.50	14.60±0.25	4.90±0.20	1.20	82.20	68.60	5639	2017	2017	2017	2017	1943	2702	3.31	3.02	2.74	2.60	3.02	3.02	28.80
EFD33.5	EFD33.5/48	2	33.50±0.50	24.10±0.20	6.20±0.20		19.10±0.20	23.50±0.40	15.35±0.25	3.80±0.15	1.70	101.40	59.60	6040	1242	1242	1242	1294	1138	1708	3.65	3.33	3.01	2.86	3.33	3.33	31.70
EFD34-1	EFD34/44	2	33.70±0.5	22.00±0.20	5.40±0.20		16.50±0.20	23.70±0.40	17.00±0.20	3.50±0.15	1.37	87.50	64.00	5600	1541	1541	1541	1605	1413	2119	3.05	2.78	2.52	2.39	2.78	2.78	26.50
EFD34-2	EFD33.7	2	34.00±0.60	23.00±0.30	5.00±0.30		18.10±0.30	24.00±0.40	17.00±0.20	2.90±0.20	2.07	102.00	49.20	5018	1018	1018	1018	1061	933	1400	2.77	2.53	2.29	2.18	2.53	2.53	24.10
EFD34-3	EPC34A1	2	33.70±0.50	23.10±0.15	5.00±0.25		18.00±0.15	23.70±0.50	17.00±0.30	3.10±0.20	1.97	101.00	51.20	5171	1070	1070	1070	1115	981	1472	2.91	2.66	2.40	2.28	2.66	2.66	25.30
EFD34-4	EFD34/22.6	2	34.00±0.60	22.60±0.20	5.60±0.30		17.60±0.20	24.00±0.40	17.00±0.30	3.00±0.20	1.80	96.10	53.40	5136	1173	1173	1173	1222	1075	1613	2.99	2.73	2.47	2.35	2.73	2.73	26.00
EFD34-6	EFD33.7/44.4/5	2	33.7±0.5	22.35±0.15	5.0±0.25		17.25±0.2	23.7±0.5/-0.4	17.0±0.2	3.1±0.1/-0.2	1.85	94.70	51.30	4856	1141	1141	1141	1189	1046	1569	2.84	2.59	2.35	2.23	2.59	2.59	24.70
EFD34-7	EFD34/44.6	2	34.00±0.60	22.30±0.20	5.60±0.30		17.10±0.20	24.00±0.40	17.00±0.30	3.00±0.20	1.83	98.70	53.94	5329	1154	1154	1154	1202	1057	1586	3.15	2.87	2.60	2.47	2.87	2.87	27.35
EFD35-1	EFD35/35B	2	35.50±0.8	17.75±0.2	6.80±0.2		13.10±0.2	26.20±0.4	16.20±0.30/-0.4	3.90±0.15	1.27	80.10	63.20	5062	1662	1662	1662	1732	1524	2286	3.02	2.76	2.50	2.37	2.76	2.76	26.30
EFD35-2	EFD35/43	2	35.70±0.7	21.50±0.3	6.60±0.2		16.50±0.2	25.20min	16.50±0.2	4.00±0.15	1.50	97.40	66.00	6428	1407	1407	1407	1466	1290	1935	3.66	3.34	3.02	2.87	3.34	3.34	31.80
EFD35-3	EFD35/40	2	35.00±0.5	20.40±0.2	8.20±0.2		16.20±0.15	26.30±0.5	14.60±0.25	4.90±0.15	1.31	92.80	70.90	6580	1612	1612	1612	1679	1477	2216	3.80	3.47	3.14	2.98	3.47	3.47	33.00
EFD35-5	EFD3535	2	35.50±0.80	17.75±0.20	6.80±0.20		13.1±0.2	26.20±0.8/-0.3	16.2±0.3/-0.4	3.90±0.15	1.27	80.10	63.20	5062	1662	1662	1662	1732	1524	2286	3.07	2.80	2.53	2.41	2.80	2.80	26.67
EFD35-6	EFD35/38	2	35.5±0.6	18.9±0.15	6.8±0.2		14.25±0.15	26.2±0.6/-0.4	16.2±0.3/-0.4	3.9±0.1/-0.15	1.36	85.06	62.70	5332	1552	1552	1552	1617	1423	2134	3.24	2.96	2.68	2.55	2.96	2.96	28.20
EFD36-1	EFD3646	1	36.0±0.60	23.0±0.20	5.8±0.20		18.2±0.20	24.0±0.40	17.0±0.20	3.0±0.20	1.70	57.20	97.50	5576	1242	1242	1242	1294	1138	1708	3.67	3.35	3.03	2.88	3.35	3.35	31.90
EFD38-1	EFD38/35	2	37.80±0.6	17.70±0.2	7.60±0.2		13.00±0.2	29.70±0.6	18.70±0.3	3.35±0.2	1.28	82.00	64.00	5248	1649	1649	1649	1718	1512	2268	3.23	2.95	2.67	2.54	2.95	2.95	28.10
EFD40-1	EFD40/45A	2	40.50±0.70	22.60±0.30	10.60±0.20		16.80±0.20	30.80min	16.30±0.20	6.60±0.10	0.97	102.82	106.51	10951	2188	2188	2188	2279	2005	3008	6.46	5.90	5.34	5.07	5.90	5.90	56.20
EFD40-2	EFD40/45B	2	40.00±0.60	22.30±0.3	8.00±0.25		17.30±0.3	29.50min	20.00±0.20	4.00±0.15	1.36	108.00	78.90	8526	1552	1552	1552	1617	1423	2134	4.66	4.25	3.85	3.66	4.25	4.25	40.50
EFD40-4	EFD40	2	39.80±0.8	27.75±0.2	20.00±0.3		22.00±0.2	28.30±0.8	19.90±0.3	11.60±0.3	0.54	121.50	226.00	27505	3910	3910	3910	4072	3584	5376	15.66	14.30	12.94	12.29	14.30	14.30	136.20
EFD40-5	EFD40.2/49.6	2	40.3±0.5	24.8±0.15	6.1±0.1/-0.2		18.1±0.15	29.4±0.6/-0.5	20.0±0.2/-0.3	3.0±0.15	1.58	104.10	65.70	6841	1336	1336	1336	1392	1225	1837	4.31	3.94	3.56	3.38	3.94	3.94	37.50



NO.	Type	尺寸(Unit : mm)									磁心参数				Al-value (nH/N <sup>2</sup> )±25%						功耗Max (W/set)						重量 (g/set)
		A	B	C	C1	D	E	F	F1	C1	Le	Ae	Ve	KP4	KP44	KP44A	KP47	KP90	KP95	KP4	KP44	KP44A	KP47	KP90	KP95		
												(mm <sup>-1</sup> )	(mm)	(mm <sup>2</sup> )	(mm <sup>3</sup> )												
EFD41-1	EFD4141	2	41.3±0.5	20.5±0.2	7.90±0.25		15.50±0.2	31.0min	19.85±0.3	3.80±0.15	1.20	92.30	77.00	7255	1930	1930	1930	2050	1900	2580	4.35	3.97	3.59	3.41	3.97	3.97	37.80
EFD41-2	EFD41/40.6	2	41.0±0.8	20.3±0.2	11.8±0.3		15.5±0.2	31.4±0.7	16.6±0.4	6.7±0.25	0.86	96.35	112.27	10817	1930	1930	1930	2050	1900	2580	6.47	5.91	5.35	5.08	5.91	5.91	56.30
EFD42-1	EFD42	2	42.50±0.5	24.75±0.2	8.00±0.2		18.50±0.2	30.00±0.5	22.00±0.3	4.60±0.15	1.10	111.00	100.00	11067	1919	1919	1919	1999	1759	2639	6.35	5.80	5.24	4.98	5.80	5.80	55.20
EFD43-1	EFD43/53	2	43.50±0.7	26.50±0.25	6.70±0.15		18.70±0.15	29.00±0.5	21.60±0.25	4.40±0.15	1.16	113.00	97.00	10976	1820	1820	1820	1896	1668	2502	6.31	5.76	5.22	4.95	5.76	5.76	54.90
EFD43.5-1	EFD43.5/44.7	2	43.50+0.60/-0.40	22.10±0.2	7.80±0.25		17.00±0.2	34.50±0.5	22.20±0.3	3.20±0.15	1.40	101.00	72.40	7312	1508	1508	1508	1571	1382	2073	4.49	4.10	3.71	3.52	4.10	4.10	39.00
EFD43.5-2	EFD43.5/54.2	2	43.5+0.6/-0.4	27.10±0.20	7.80±0.25		22.00±0.20	34.50±0.50	22.20±0.30	3.20±0.15	1.68	121.80	72.40	8818	1517	1517	1517	1517	1459	2072	5.35	4.88	4.42	4.20	4.88	4.88	46.50
EFD43.7-1	EFD43.7/57	2	43.70±0.7	28.50±0.2	6.20±0.25		21.50±0.2	29.50min	20.30±0.3	4.00±0.2	1.50	124.50	82.80	10309	1407	1407	1407	1466	1290	1935	5.90	5.39	4.87	4.63	5.39	5.39	51.30
EFD45-1	EFD45/49	2	45.20±0.8	24.70±0.2	5.90±0.2		18.00±0.2	33.10±0.6	24.00±0.4	3.00±0.15	1.54	112.70	73.10	8240	1371	1371	1371	1428	1257	1885	4.69	4.28	3.88	3.68	4.28	4.28	40.80
EFD46-1	EFD46/60A	1	46.00±0.55	30.00±0.25	12.00±0.15		24.00±0.20	36.00±0.50	20.00±0.20	6.00±0.15	1.09	135.00	124.00	16688	1937	1937	1937	2018	1775	2663	9.55	8.72	7.89	7.49	8.72	8.72	83.00
EFD46-3	EFD4649	2	46.20±0.60	24.60±0.20	5.90±0.25		17.90±0.20	34.30±0.60	24.00±0.2/-0.3	2.95±0.20	1.45	105.00	72.60	7623	1460	1460	1460	1521	1338	2007	4.77	4.36	3.94	3.75	4.36	4.36	41.50
EFD46-4	EFD4649A	2	45.50±0.80	24.45±0.15	6.50±0.20		17.85±0.15	33.00min	22.75±0.4/-0.3	3.30±0.20	1.44	106.70	77.70	8291	1829	1829	1829	1829	1759	2482	5.15	4.70	4.26	4.04	4.70	4.70	44.80
EFD47-1	EFD47/60	5	47.00±0.55	30.10±0.25	12.00±0.25		24.10±0.20	36.00±0.50	19.55±0.25	6.00±0.15	1.06	135.50	127.00	17238	1992	1992	1992	2075	1826	2739	9.83	8.98	8.12	7.72	8.98	8.98	85.50
EFD50-1	EFD50/50B	6	50.00±0.70	25.25±0.30	8.00±0.20		18.50±0.20	36.00min	26.40±0.30	3.90±0.2	1.15	118.80	103.50	12295	1836	1836	1836	1912	1683	2524	6.90	6.30	5.70	5.42	6.30	6.30	60.00
EFD50-2	EFD5050	1	50.7±0.7	25.9±0.25	9.0±0.35		18.9±0.20	38.1±0.7	23.4±0.3	5.0±0.2	1.01	116.06	115.00	13329	2090	2090	2090	2177	1916	2874	8.17	7.46	6.75	6.41	7.46	7.46	71.00
EFD50-4	EFD5054	2	50.4±1.0	26.9±0.20	5.5±0.20		20.2±0.20	36.3min	28.8±0.40	2.6±0.20	1.58	116.62	74.00	8626	1336	1336	1336	1392	1225	1837	5.34	4.87	4.41	4.19	4.87	4.87	46.40
EFD50-3	EFD5056	2	50.0±0.6	28.0±0.3	6.1+0.1/-0.2		20.6±0.3	34.0min	24.0±0.3	3.2+0.05/-0.2	1.50	119.30	81.80	9765	1407	1407	1407	1466	1290	1935	6.21	5.67	5.13	4.87	5.67	5.67	54.00